

MATERIAL

BESPOKE STONE + TILE



ROYAL MARBLE

SOURCE: NORTH AMERICA

Royal Marble is energetic but refined, moving fluidly between gray veining on a field of white, and white accents against a soft gray base.

TECHNICAL DATA

ASTM 97 DENSITY	170 lbs/ft ³
ASTM 97 ABSORPTION	.06%
ASTM C170 COMPRESSIVE STRENGTH	16,338.45 lbs/in ² wet
ASTM C880 FLEXURAL STRENGTH	--- lbs/ft ² wet
ASTM 353 ABRASION RESISTANCE	--- lbs/ft ³

AVAILABLE APPLICATIONS

ARCHITECTURAL ELEMENTS
MOLDING
TILE
MOSAICS

CONSIDERATIONS

FREEZE / THAW	APPROVED
SALT WATER	APPROVED
VARIATION	HIGH
ACCEPTABLE TRAFFIC	HIGH

CARE AND MAINTENANCE

- High acid sensitivity is a property of marble. Care must be taken in the presence of acidic foods and cleaning products.
- Low abrasion resistance is inherent in most marbles. Light scratching will occur with exposure to abrasives. A patina will result over time. Doormats are recommended when used as flooring.
- This marble has a low to moderate absorption rate. It is recommended to seal this material prior to use to allow for additional time to “clean up” the spill, before it has time to result in a stain.

EXPLOREMATERIAL.COM

ATLANTA | AUSTIN | CHICAGO | COSTA MESA | DALLAS | DENVER | HOUSTON | SAN ANTONIO